

**Claims**

1. A paving composition comprising aggregate and asphalt characterized in that:
  - a) a major proportion of the composition by weight is aggregate; and
  - b) a minor proportion of the composition by weight is asphalt.
- 5 2. A paving composition as claimed in claim 1 in which the asphalt is present as a mastic.
3. A paving composition as claimed in claim 2 in which the asphalt mastic comprises
- 10 additives to provide enhanced stability and drainability.
4. A paving composition as claimed in claim 1 in which the aggregate comprises particles of a size such that at least 80 percent will be retained on a 2 mm sieve passing 19 or 20 mm sieve sizes, and about 60 to 75 percent will be retained on a 7 mm sieve passing 19 or
- 15 20 mm sieve sizes.
5. A paving composition as claimed in claims 1 or 4 in which the aggregate is granite, basalt, quartzite, industrial slag, crushed bottles, crushed concrete, or sand and sludge stones from domestic wastes.
- 20 6. A paving composition as claimed in claim 3 in which the asphalt mastic comprises additives selected from the group consisting tire powder, latex powder, rock filler, slag filler and cellulose fibre.
- 25 7. A paving composition as claimed in claim 6 in which the tire or latex powders are of sizes 30 to 50 microns in a proportion of between 2 and 10 percent by weight of asphalt and cellulose fibre pellets that form the asphalt mastic.
8. A paving composition as claimed in claim 6 in which the rock or slag fillers are
- 30 present in a proportion of between 4 and 10 percent by weight of aggregates.

9. A paving composition as claimed in claim 6 in which the cellulose fibre is selected from the group consisting oil palm fibre, coconut fibre, kenaf fibre, rubber-wood fibre and paper pulp fibre.

5 10. A paving composition as claimed in claim 9 in which the cellulose fibre is mechanically pelletized with light asphalt emulsions or any other suitable materials.

11. A paving composition as claimed in claim 10 in which the proportion of asphalt emulsion to coat the cellulose fibres is between 10 and 40 percent by weight of fibres.

10

12. A method of producing a paving layer, which comprises applying a composition according to any one of claims 1 to 11 to a substrate and curing the asphalt such that the aggregate in the paving layer is bonded together by cured solid asphalt.

15

13. A paved layer which has been produced by a method according to claim 12.

Copyright Clearance Center